

Application No.: 10/621,399

Docket No.: 21581-00298-US1

AMENDMENT TO THE SPECIFICATION

Please amend Table 7 in the specification at page 36, beginning at line 14 to read as follows:

Table 7

	Catalyst	Cyclooctene oxide yield (%)	Tungsten leaching (%)	Relative rate of leaching (%)
Example 31	$\gamma\text{-Fe}_2\text{SiW}_{10}\text{O}_{38}/\text{Zn-SnO}_2$	13	0	0
Example 32 Compar. Example 8	$\gamma\text{-Fe}_2\text{SiW}_{10}\text{O}_{38}/\text{SnO}_2$	8	0	0
Compar. Ex. 8 Compar. Ex. 9	W/SnO ₂	5	0.05	—